

Edgetek™ AT Acetal (POM) Compounds

The Edgetek™ AT product family is a range of unfilled, filled and impact grade acetal (POM) compounds. Using POM homopolymer or copolymer as the base resin, these materials offer a wide range of physical properties. Edgetek AT compounds are available pre-colored or can be colored during the manufacturing process with concentrates such as PolyOne's OnColor™ masterbatches.

The inherent crystallinity of Edgetek AT provides high strength, stiffness and hardness; good chemical and environmental resistance; low friction and wear; and low moisture absorption. Take into account that as many resins acetal has poor resistance to chlorine an oxidizing environment. Edgetek AT is available in a standard range or can be custom-formulated to meet your specific product and design requirements. Grades are available for both injection molding and extrusion applications. All compound grades are UV stabilized.

This document provides general advice on molding processes for the use with Edgetek™ AT compounds. The information provided in this document is intended only as a guide to use together with your past experience of molding techniques where applicable, using these materials. Our staff will be will be happy to assist in any areas where this guide does not provide a satisfactory solution.

Injection molding parameters

The barrel temperatures below should be used as a reference point. Actual melt temperatures should be measured using a pyrometer to ensure consistent and accurate processing.

	Edgetek ATH POM HOMOPOLYMER	Edgetek ATC POM COPOLYMER
Barrel Temperatures	Metric	Metric
Rear Zone	180 – 190 °C	180 – 190 °C
Center Zone	190 – 200 °C	180 – 190 °C
Front Zone	200 – 210 °C	190 – 200 °C
Nozzle Temperature	210 – 215 °C	200 – 210 °C
Melt Temperature	210 – 220 °C	195 – 210 °C
Mold Temperature	80 – 100 °C	75 – 100 °C
Back Pressure	< 4 Mpa	< 3 Mpa
Screw Speed	50 – 90 rpm	50 – 90 rpm
Injection Speed	100 – 300 mm/s	100 – 300 mm/s
Injection Pressure	60 – 150 Mpa	60 – 150 Mpa
Hold Pressure	80 – 100 Mpa	80 – 100 Mpa
Cooling Time	10 – 15 seconds	10 – 15 seconds
Cushion	3 – 6 mm	3 – 6 mm
Screw Type	General – Purpose Screw L/D Ratio = 18:1 - 22:1	General – Purpose Screw L/D Ratio = 18:1 - 22:1
Compression Ratio	2,0:1 – 3,0:1	2,0:1 – 3,0:1
Nozzle	General Purpose	General Purpose

Startup & Shutdown recommendations

Drying	Drying Edgetek AT is not required, but always recommended, as will avoid marks on the surface of the parts and injection problems EDGETEK ATH (POM Homopolymer) should be dried at 80-85°C for 3h. EDGETEK ATC (POM Copolymer) should be dried at 80-100°C for 4h.
Purge Compound	HDPE or HIPS
Shutdown	The recommended startup and shutdown procedures for Edgetek AT products begin and end by purging the equipment with a general purpose HDPE or HIPS resin. All tooling and equipment must be free from any residual Edgetek AT upon shutdown. Continue generating parts made from the natural HDPE or HIPS until clear. When using a hot runner system, care must be taken to remove residual product from the manifold.
Coloring	Contact your PolyOne Representative.
Recycling	Edgetek AT is fully recyclable. Conventional granulators with sharp blades should be used. Consistent regrind usage of up to 10% is permissible. Excessive fines or dust-like particles should be avoided.

CONTACT INFORMATION

Europe

Germany – Gaggenau
+49 (0) 7225 680 20

Spain – Barbastro
+34 (0) 97431 0314

Turkey – Istanbul
+90 (0) 212 549 2241

Americas

U.S. – Avon Lake, Ohio
+1 440 930 1000

Asia

China – DongGuan
+86 (0) 769 8587 8800

China – Shenzhen
+86 (0) 755 2969 2888

India – Mumbai
+91 9820 194 220

Singapore
+65 (0) 6861 9325



*Beyond Polymers.
Better Business Solutions.™*

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, OH 44012
U.S.A.
Tel.: +1 440 930 1000

PolyOne Asia

Guoshoujing Road No. 88
Z.J Hi-Tech Park, Pudong
Shanghai, 201203, China
Tel.: +86 (0) 21 5080 1188

PolyOne Europe

Rue Melville Wilson 2
5330 Assesse, Belgium
Tel.: +32 (0) 83 660 211

Copyright © 2007, PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne’s products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.